

Raychem

Product description

BPTM is a medium wall, heat-shrinkable tubing which provides insulation enhancement and protection against flashover and accidentally induced discharge.

Particularly useful in confined spaces BPTM tubing can be used on both circular and rectangular copper or aluminium busbars.

On application of heat the tubing shrinks snugly over the busbar profile ensuring that the required minimum wall thickness is obtained.

BPTM tubing can be installed easily during large scale production using an oven or in the field using a gas torch or hot air.

BPTM tubing is manufactured from a non-halogen based polymer which has excellent performance in high voltage environments and greatly reduces the noxious and corrosive effects in fire situations.

Applications

The use of BPTM tubing allows equipment designers the freedom to reduce air spacing between busbars, such as in the manufacture of switchgear cabinets where space is at a premium. BPTM provides flashover protection up to 25 kV.

Clearance reduction

The table below indicates the clearance reductions which are possible using BPTM tubing. These are derived from BIL, AC withstand, DC withstand and discharge extinction tests.

These clearances should not be adopted without testing by the user. Sharp electrodes and unusual geometries may require wider clearances.

Rated voltage (kV)	Phase – phase (mm)	Phase – ground (mm)	IEC 71-2 air clearance (mm)
Round busbars			
12	55	65	120
17.5	70	85	160
24	95	125	220
36	150	205	320
Rectangular busbars			
12	65	75	120
17.5	85	104	160
24	115	150	220
36	200	285	320

BPTM

Heat-shrinkable busbar insulation tubing

Voltage class 25 kV

Application Ø 6.5 – 190 mm



Features/benefits

- Compatible with all other products in the Raychem MV insulation enhancement system
- Excellent flexibility, can be installed on a wide range of curved or bent busbars without cracking or creasing
- High shrink ratio reduces inventory and simplifies product selection
- Exceptional insulation and long term reliability even at high continuous operating temperatures
- Extremely durable, resists damage from solvents, ultraviolet light, weathering, mechanical impact and general wear and tear
- Suitable for indoor and outdoor use
- Excellent anti-tracking properties
- Good thermal emissivity and contact with busbars means no derating is required
- Flame retardant and non-halogen based material reduces flammability and the toxic and corrosive effects in fire situations
- Can be stored indefinitely at temperatures up to 50°C without loss of performance
- Over 20 years of successful operating experience

BPTM


Heat-shrinkable busbar insulation tubing

Key product specifications	Test method	Requirement
Thermal endurance	IEC 216	105°C min.
Accelerated ageing	ISO 188, ASTM D2671	168 hrs @ 120°C
- Tensile strength		10 MPa min.
- Ultimate elongation		300% min.
Comparative tracking index	IEC 112, VDE 0303/1	KA 3c
Dielectric strength	ASTM D149, IEC 243	180 kV/cm min. @ 2 mm 150 kV/cm min. @ 2.5 mm 120 kV/cm min. @ 3 mm
Low temperature flexibility	ASTM D2671 Procedure C	No cracking after 4 hrs @ -40°C
Smoke index	NES 711	Less than 120
Acid gas generation	Raychem PPS 3010 4.23	Less than 1% by weight

Note: For further product specification information see Raychem PPS 3010/04.

Product selection


BPTM should normally be used on the following busbar sizes



Product size

	Rectangular bars, L + T (mm)		Round bars, D (mm)	
	min.	max.	min.	max.
BPTM 15/6	12	18	6.5	12
BPTM 30/12	22	38	13.5	25
BPTM 50/20	36	65	22	43
BPTM 75/30	55	95	33	63
BPTM 100/40	70	130	44	86
BPTM 120/50	90	165	55	105
BPTM 175/70	125	235	80	150
BPTM 205/110	200	276	127	190
BPTM 235/130	235	315	150	220

Ordering information



Ordering description

Ordering description	Inside diameter (mm)		Wall thickness (mm)		UOM: m spool length
	H min.	h max.	W nom.	w min.	
BPTM 15/6-A/U	15	6	1.1	1.90	30
BPTM 30/12-A/U	30	12	1.1	2.20	30
BPTM 50/20-A/U	50	20	1.1	2.35	30
BPTM 75/30-A/U	75	30	1.1	2.35	20
BPTM 100/40-A/U	100	40	1.1	2.35	25
BPTM 120/50-A/U	120	50	1.3	2.80	25
BPTM 175/70-A/U	175	70	1.3	2.80	15
BPTM 205/110-A/U	205	110	1.3	2.80	10
BPTM 235/130-A/U	235	130	1.5	3.10	20

Note: Dimensions in mm unless otherwise stated. W, H = as supplied, w, h = after free recovery. Maximum longitudinal change after free recovery: + 5% -10%. Maximum eccentricity (as supplied): 40%, (after free recovery) ≤ 75/30 10% ≥ 100/40 15%. Fit the larger size of BPTM if two sizes fit the required application. Installation instructions EPP 0618 5/96 and Material Safety Data Sheet available on request.

Technical reports

- UVR 8019 – (Rev 1) Qualification report of BPTM tubing
- UVR 8016 – Testing of BPTM dust pick-up and comparison of BPTM cleaning techniques
- UVR 8091 – Production-scale installation of BBIT/BPTM
- UVR 8122 – Resistance of BBIT/BPTM to hydrofluoric acid
- UVR 8194 – Long term weathering and thermal ageing of BBIT and BPTM tubing

All of the above information, including drawings, illustrations and graphic designs, reflects our present understanding and is to the best of our knowledge and belief correct and reliable. Users, however, should independently evaluate the suitability of each product for the desired application. Under no circumstances does this constitute an assurance of any particular quality or performance. Such an assurance is only provided in the context of our product specifications or explicit contractual arrangements. Our liability for these products is set forth in our standard terms and conditions of sale. ALR, AMP, Cevolit, Cevosil, Critchley, Dorman Smith, Dulmison, Hellstern, La Prairie, Morlynn, Raychem, and SIMEL are trademarks of Tyco International Ltd.

tyco

Electronics

Energy Division



AMP

Cevolit

Cevosil



Hellstern



MORLYNN INSULATORS

Raychem

SIMEL

Argentina

Phone: ++54-11-4733 2277
Fax: ++54-11-4733 2267

Australia

Phone: ++61-2-4390 1111
Fax: ++61-2-4353 2497

Brazil

Phone: ++55-11-861 1311
Fax: ++55-11-861 1862

Canada

Phone: ++1-905-475 6222
Fax: ++1-905-470-4453

France

Phone: ++33-3-80583200
Fax: ++33-3-80341015

Mexico

Phone: ++52-5-729 0405
Fax: ++52-5-361-8545

Thailand

Phone: ++66-2-7394026 - 32
Fax: ++66-2-3260563 - 64

United States of America

Phone: ++1-800-327-6996
Fax: ++1-800-527-8350

Tyco Electronics Raychem GmbH

Energy Division
Haidgraben 6, 85521 Ottobrunn/Munich, Germany
Phone: ++49-89-6089-0, Fax: ++49-89-6096345

<http://energy.tycoelectronics.com>